

PINEAPPLE CONTRACTS UNLIMITED TEST REPORT

SCOPE OF WORK

CALIFORNIA TB-133 – FLAMMABILITY TEST PROCEDURE FOR SEATING FURNITURE FOR USE IN PUBLIC OCCUPANCIES

REPORT NUMBER

103179016GRR-001

ISSUE DATE

03-Aug-17

PAGES

9

DOCUMENT CONTROL NUMBER RT-AMER-L-GRR-DUR-001

© 2017 INTERTEK





Total Quality. Assured. TEST REPORT FOR PINEAPPLE CONTRACTS UNLIMITED

Report No.: 103179016GRR-001

Date: 03-Aug-17

4700 Broadmoor Ave SE, Suite 200 Kentwood, MI 49512

Telephone: +1 616 656 7401 Facsimile: +1 616 656 2022

www.intertek.com

SECTION 1

CLIENT INFORMATION

Attention: Neill Smith Pineapple Contracts Unlimited Westmead, Aylesford

ME20 6XJ United Kingdom

Phone: 44 (0) 1622 237830

Email: Neill.Smith@PineappleContracts.com

Eric Frees Test Engineer

Project Reviewer

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

Rev. Date: 5/31/17, Doc. # RT-AMER-L-GRR-DUR-001

Page 2 of 9

TEST REPORT FOR PINEAPPLE CONTRACTS UNLIMITED Report No.: 103179016GRR-001

Date: 03-Aug-17

SECTION 2

SUMMARY AND CONCLUSION

Date Received: 27-Jul-17
Dates Tested: 01-Aug-17

DESCRIPTION OF SAMPLES (PER PINEAPPLE CONTRACTS UNLIMITED)

Product: Ryno Dining Chair

Model Number: N/A
Fabric Type: N/A
Fabric Color: N/A
Inter-liner/Blocking Layer: N/A
Fill Description: N/A

Condition of Samples: Production

WORK REQUESTED/APPLICABLE DOCUMENTS

CALIFORNIA TB-133 – FLAMMABILITY TEST PROCEDURE FOR SEATING FURNITURE FOR USE IN PUBLIC OCCUPANCIES

Intertek quote Qu-00806895

CONCLUSION

TEST	RESULTS
CALIFORNIA TB-133 – FLAMMABILITY TEST PROCEDURE FOR SEATING FURNITURE FOR USE IN PUBLIC OCCUPANCIES	CONFORMING

SAMPLE DISPOSITION

Sample tested and destroyed.

TEST EQUIPMENT:

ASSET NUMBER	EQUIPMENT	CALIBRATION DATE	CALIBRATION DUE
138051.26	CARBON MONOXIDE / DIOXIDE ANALYZER	VBU	VBU
138051.18	OXYGEN ANALYZER	03/06/2017	03/06/2018
138245	SCALE	07/30/2016	07/30/2017
138051.33	FLOW METER 0-14 SLM PROPANE	11/09/2016	11/09/2017
138181	DPI DIFFERENTIAL PRESSURE TRANSDUCER	09/27/2016	09/27/2017
138327	GRADUATED RULE 36"	10/11/2017	10/11/2018
138412	STOPWATCH	03/14/2017	03/14/2018
138406	TEMP/HUMIDITY PROBE	09/28/2016	09/28/2017
138051.9	SMOKE DENSITY MONITOR 0-100%	VBU	VBU

Rev. Date: 5/31/17, Doc. # RT-AMER-L-GRR-DUR-001 Page 3 of 9

TEST REPORT FOR PINEAPPLE CONTRACTS UNLIMITED Report No.: 103179016GRR-001

Date: 03-Aug-17

SECTION 3

CALIFORNIA TB-133 – FLAMMABILITY TEST PROCEDURE FOR SEATING FURNITURE FOR USE IN PUBLIC OCCUPANCIES

Date Received: 27-Jul-17
Date Tested: 01-Aug-17

Location Tested: Intertek Kentwood, MI

Room Temperature (Start): 75°F Room Humidity (Start): 55% Minutes out of Conditioning: 5.0


PRODUCT: RYNO DINING CHAIR

CRITERIA	LIMIT	VALUE	PASS/FAIL
Flame Out (min:sec)	N/A	1:45	N/A
8' Temp. Increase (Maximum), °F	≤ 200°F	79.4°F	Pass
4' Temp. Increase (Maximum), °F	<u>≤</u> 50°F	2.6°F	Pass
4' Smoke Opacity (Maximum), %	<u><</u> 75 %	14%	Pass
CO Concentration (Maximum), ppm	N/A	29ppm	N/A
Time CO Is Greater Than 1000ppm (min:sec)	< 5:00	0:00	Pass
Maximum Rate of Heat Release	<u><</u> 80 kW	20 kW	Pass
Total Heat Energy in First 10 Min.	≤ 15 MJ	1.7 MJ	Pass
Pre-Test Weight	N/A	127.80 lbs	N/A
Weight Loss at 10 Minutes	<u>≤</u> 3 lbs	0.00 lbs	Pass
Post-Test Weight	N/A	127.80 lbs	N/A


The submitted sample met the acceptance criteria of the test described above. Refer to the following pages for charts and photographs.


Rev. Date: 5/31/17, Doc. # RT-AMER-L-GRR-DUR-001

8' Thermocouple Temperature




4' Thermocouple Temperature







Room Carbon Monoxide



Rate of Heat Release



Sample Weight (scale reading)





RYNO DINING CHAIR - Pre-Test Setup



RYNO DINING CHAIR - Post-Test

TEST REPORT FOR PINEAPPLE CONTRACTS UNLIMITED Report No.: 103179016GRR-001

Date: 03-Aug-17

SECTION 4

REVISIONS MADE TO TEST REPORT

DATE	REVISION DESCRIPTION	REVISED BY	REVISED BY
03-Aug-17	Initial release.	Eric Frees	EI

Page 9 of 9